

Characteristic (RSS)	India (RSS 1x)	Indonesia (RSS 1)	Thailand (RSS 1)	Thailand (RSS 3)	Vietnam (RSS 3)	Thailand (RSS 5)
Dirt content on 44u aperture, max %wt	0.01	0.026	0.019	0.024	0.014	0.092
Ash content, max %wt	0.31	0.28	0.35	0.45	0.384	0.39
Nitrogen, max % wt	0.40	0.27	0.53	0.37	0.46	0.51
Volatile matter, max %wt	0.42	0.26	0.53	0.86	0.32	0.49
Wallace rapid plasticity (Po), min	41	50-52	40	34	52.2	45
Plasticity retention index (PRI), min %	100	80	86.3	95.6	72.4	96.7
Mooney Viscosity ML(1'+4') 100 C	67	N/A	69.5	62.7	81.1	78.3

This grade falls under the VGR category (Visually Graded Rubber) for which there are no standard specifications. The values given above are only for reference purposes.