

Characteristic (TSR CV60)	Indonesia (SIR CV60)	Vietnam (SVR CV60)	Malaysia (SMR CV60)
Dirt content on 44u aperture, max %wt	0.03	0.02	0.02
Ash content, max %wt	0.5	0.40	0.50
Nitrogen, max % wt	0.6	0.60	0.60
Volatile matter, max %wt	0.6	0.80	0.80
Wallace rapid plasticity (Po), min	30	-	-
Plasticity retention index (PRI), min %	60	60	60
Mooney Viscosity ML(1'+4') 100 C	60+/-5	60+/-5	60+5/-5