

Characteristic (TSR L)	Thailand (STR 5L)	Indonesia (SIR 3L)	Vietnam (SVR 3L)	Malaysia (SMR L)
Dirt content on 44u aperture, max %wt	0.04	0.03	0.03	0.02
Ash content, max %wt	0.40	0.50	0.50	0.50
Nitrogen, max % wt	0.60	0.60	0.60	0.60
Volatile matter, max %wt	0.80	0.80	0.80	0.80
Wallace rapid plasticity (Po), min	35	30	35	35
Plasticity retention index (PRI), min %	60	75	60	60
Lovibond Colour: individual value (max)	6.00	6.00	6.00	6.00
Lovibond Colour: individual range (max)	2.00	2.00	2.00	2.00